## **epostuk** 01/25 107



## EPOSTUK

Two-component epoxy sealant featuring high chemical resistance and workability for 2 to 20 mm joints. Ideal for industrial environments subject to aggressive chemicals.

## groutings and sealants





# epostuk





## **MAIN FEATURES**

High resistance to aggressive chemicals Optimum workability High mechanical strength High degree of hardness Optimum cleanability

## APPEARANCE

Comp. A-thick paste in 2 colours (see colour card in www.technokolla.com) Comp. B-viscous liquid

## STORAGE

24 months in dry place at temperatures from +10 to +30°C

### **FIELDS OF USE**

- Grouting the joints in ceramic or stone\* floors or walls, e.g.: porcelain stoneware, split tiles, ceramic or marble mosaic. In places or on surfaces subject to aggressive chemicals, such as: dairies, laboratory tables, tanneries, paper-mills, industrial kitchens, slaughterhouses, wine-making enterprises, etc.
- Grouting the joints in floors subject to heavy traffic, industrial storehouses, shopping centers, etc. EPOSTUK can be used as adhesive (class R2T in accordance with EN12004) for glueing the above mentioned cladding materials to iron and fiberglass reinforced plastic.
- Suitable for grouting swimming pools, also when filled with seawater.
- \* To make sure the colour does not change, it is advisable to perform a cleanability test before grouting natural stone materials.

## NATURE OF THE PRODUCT

EPOSTUK consists of two components containing epoxy resins, quartz charges and specific additives.

For further details, ask the technical office for the safety brief or download it from the web site www.technokolla.com.

## HOW TO PREPARE THE MIXTURE

EPOSTUK is a "reactive" sealant. This means that it sets through chemical reaction between two components, A and B. It is very important to thoroughly mix these components together.

Start by pouring the liquid (comp. B) onto the paste (comp. A), then stir using a blender with a spiral whisk attachment.

The reaction developed by these products is exothermic (heat develops). Remember that if the components are stirred at high speed, the heat developed will considerably speed up the hardening process and, thus, shorten the time the product can be worked.

The creamy paste obtained can be easily applied by trowel.

#### groutings and sealants



## **RECOMMENDED ACCESSORIES**



Soft white felt



Trowel



Handle for sponges and felts





Washing trough with 3 rollers

## **GROUTING OPERATION**

Apply EPOSTUK with a rubber trowel, and make sure that the joints are filled completely. Wipe off any excess sealant with the edge of the applicator.

Squeeze a sponge soaked in water over the grouted surface and emulsify the product with medium-hard felt by making circular movements over the surface. Take care not to empty the joint. Excess product can be easily removed with a soft rubber scraper. After cleaning, it is very important for the tile surface to be completely free from traces of grouting as it is very difficult to remove once hardened. Frequently rinse the sponge with clean water when cleaning.

## **AVAILABLE COLOURS**

00 WHITE 01 MANHATTAN

## WARNINGS AND RECOMMENDATIONS

- Do not attempt to use random percentages of the product: incorrect catalysis ratio will compromise the hardening process
- Do not use the product after it becomes difficult to apply. Prepare fresh mixture
- Wear rubber gloves at all times when using the product.
- The consumption data refer to the following types of tiles: Single-fired tiles, Split tiles, Porcelain stoneware. Do not use on porous surfaces (e.g.: cotto)
- Do not use EPOSTUK when there is water in the joints
- Do not use for grouting that is subject to movements
- Do not wash with acids or strong oxidants during application

GROUTING CONSUMPTION g/m <sup>2</sup>									
TILE	JOINT in mm								
in cm	3	5	8	10	12	15			
10x10x0.6	580	960	1550	1900	2300	2900			
7.5x15x0.7	680	1100	1800	2200	2700	3400			
15x15x0.9	580	960	1550	1900	2300	2900			
12x24x0.9	540	900	1400	1800	2150	2700			
12x24x1.4	840	1400	2200	2800	3400	4200			
20x20x0.9	430	720	1150	1400	1700	2200			
20x20x1.4	670	1100	1800	2200	2700	3400			
20x30x0.9	360	600	960	1200	1400	1800			
30x30x1	320	530	850	1100	1300	1600			
30x30x1.4	450	750	1200	1500	1800	2200			
30x60x1	240	400	640	800	960	1200			
40x40x1	240	400	640	800	960	1200			
50x50x1	190	320	510	640	770	960			
60x120x1.1	130	220	350	440	530	660			

## CONSUMPTION CALCULATION FORMULA

x 160 =  $\frac{g}{m^2}$ 

 $A \times B \times \begin{bmatrix} C + D \\ C \times D \end{bmatrix}$ 



## epostuk

TECHNICAL DATA	VALUE	REQUIREMENT	STANDARD
Mixing ratio	(A:B) 94:6		
Temperature during application	min. +12°C, max +25°C		
Weight density of mixture	~ 1.6 kg/l		
Pot life	*40 min		
Treadable	* after 24 h		
Surface can be used	* after 3 days		
Thermal resistance	**from -20 °C to 100°C		
Abrasion resistance	~ 150 mm <sup>3</sup>	≤ 250 mm³	EN 12808-2
Flexural strength after dry storage	≥ 30 N/mm²	≥ 30 N/mm²	EN 12808-3
Compressive strength after dry storage	≥ 45 N/mm²	≥ 45 N/mm²	EN 12808-3
Shrinkage	≤ 1.5 mm/m	≤ 1.5 mm/m	EN 12808-4
Water absorption after 240 min.	≤ 0,1 g	≤ 0.1 g	EN 12808-5
Initial bond	~ 5.6 N/mm <sup>2</sup>	≥ 2 N/mm²	EN 12003
Bond after immersion in water	~ 7.4 N/mm²	≥ 2 N/mm²	EN 12003
Bond after thermal shock	~ 2.5 N/mm <sup>2</sup>	≥ 2 N/mm²	EN 12003
Сгеер	≤ 0.5 mm	≤ 0.5 mm	EN 1308
Open time	* 20 min.	° 20 min.	EN 1346

° according to standard "EN 12004"

\* these times refer to a temperature of 23°C-50% R.H.. They are shorter at higher temperatures and longer at lower temperatures.

\*\* the maximum temperature is to be understood as an occasional service and not as a continuous one.

## SPECIFICATION

Ceramic floor and wall tiles must be grouted using epoxy-based sealant with high chemical resistance such as Technokolla's EPOSTUK, which can be used to seal joints up to 20 mm.

**Technokolla** reminds you to examine the "**notes**" document that completes the information in this data sheet. The document can be downloaded in the pdf format from the website www.technokolla.com.

The advice about technical matters in the technical data sheets, or given verbally or in writing by our personnel as part of our customer assistance service, is the result of our best and most up to date experience. Since we are unable to personally modify the conditions in the building site or the way the work is carried out, this information is purely indicative and, thus, binds us neither legally nor in any other way in relation third parties. This information does not relieve the end user from being responsible for testing our products so as to make sure they are fit for the required use. We therefore strongly advise the customer/user to subject Technokolla's products to preventive tests in order to ensure that they are suitable. The end user is also responsible for checking to make sure that this technical data sheet is not obsolete and that more recent editions have not replaced it. Thus, before using our products, you are advised to download the most up to date version of the technical data sheet from our web site www.technokolla.com.

## epostuk

CHEMICAL RESISTANCE OF CERAMIC TILING GROUTED WITH EPOSTU

## **TECHNICAL DATA**

GROUP	NAME	<b>CONCENTRATION %</b>	CONTINUOUS SERVICE 20°C	DISCONTINUOUS SERVICE 20°C
ACIDS				
	Acetic	2,5	-	(+)
	ш	5	-	-
	ű			
	Hydrochloric	37	(+)	+
	Chromic	20	-	-
	Citric	10	-	-
	Formic	2,5	-	(+)
	u .	10	-	-
	Lactic	2,5	-	(+)
	"	5	-	-
	"			
	Nitric	25	(+)	+
	"	50	-	-
	Oleic			-
	Phosphoric "	50	-	(+)
		75	-	-
	Sulphuric "	1,5	+	+
	u u	50	(+)	+
		98	-	-
	Tannic	10	(+)	+
	Tartaric	10	(+)	+
		10	+	+
ALKALIS A	ND SATURATED SOLUTI		+	
	Ammonia	25		+
	Caustic soda Potash	50 50	+	+
		50	-	(+)
	Sodium hypochlorite Active chlorine	6,5 g/l	(+)	+
	Active chlorine	162 g/l	(+)	-
SATURATE	D SOLUTIONS	102 9/1	·	•
SATURALE	Sodium hyposulphite		+	+
	Sodium chloride		+	+
	Calcium chloride		+	+
	Iron chloride		+	+
	Aluminium sulphate		+	+
	Sugar		+	+
	Hydrogen peroxide	1	(+)	+
	"	10	(+)	+
	Sodium bisulphite		(+)	+
OILS AND F				
	Gasoline		+	+
	Petroleum		+	+
	Diesel fuel		+	+
	Olive oil		+	+
SOLVENTS				
	Ethyl alcohol	15	-	(+)
	Acetone		-	-
	Glycol		+	+
	Glycerine		+	+
	Perchloroethylene		-	-
	Trichloroethane		-	-
	Trichloroethylene		-	-
	Methylene chloride		-	-
	Toluol		-	-
	Benzol		-	-
	Xylol		-	-
KEY:	+ Optimum resistance	(+) Fair resistance	- Poor resistance	
·	• Optimum resistance	(') an resistance	- 1 001 1031310100	

**Technokolla** reminds you to examine the "**notes**" document that completes the information in this data sheet. The document can be downloaded in the pdf format from the website www.technokolla.com.



Sika Italia S.p.A. Registered Office and Administrative Headquarters: Via L. Einaudi 6, 20068 Peschiera Borromeo (MI) Sassuolo plant (MO): Via Radici in Piano 558, Postal Code 41049

Ph.: +39 0536 809711 Fax: +39 0536 809729 www.technokolla.com