

PLAN-10

High-performance, ultra-quick setting selfleveling mortar used in layers 2 to 10 mm thick.

substrate preparation





plan-10



ECHNOKOLLA

PLAN-10

BUTCHERLA

MAIN FEATURES

Monocomponent High mechanical strength Optimum bonding capacity Ultra-fast setting Layers up to 10 mm thick Very smooth surface Can be pumped

APPEARANCE

Reddish powder

STORAGE


8 months in dry place

FIELDS OF USE

- Leveling indoor floors in layers 2 to 10 mm thick before fixing floor cladding in moderately, or heavily trafficked new or renovated places with UPEC P2 and P3 classifications.

SUBSTRATES

Cement-based screeds, quick-setting screeds, concrete, floors in PVC, linoleum, vinyl materials, anhydrite screeds, old ceramic or marble floors, water-or electric heating screeds. Note: consult table for preliminary treatment:



X = treatment required

CLADDING MATERIALS

Ceramic or natural stone tiles, carpeting, plastic cladding materials, glued or floating parquet, paint and linoleum.



substrate preparation

RECOMMENDED ACCESSORIES



437185 Flat trowel

NATURE OF THE PRODUCT

PLAN-10 mainly consists of high-strength cements, selected quartz mineral charges, organic copolymers and specific additives.

For further details, ask the technical office for the safety brief or download it from the web site www.technokolla.com.

APPLICATION

Before PLAN-10 is applied, it is very important to make sure that the substrate is stable and compact. It must also be clean, dust-free and pretreated, as indicated in the table on page 2.

For further details about how to prepare substrates, consult the "notes" document, which can be downloaded from the website www.technokolla.it.

HOW TO PREPARE THE MIXTURE

Blend PLAN-10 with approximately 6 l. of clean water per 25 kg bag (24±1%) until mixture is homogeneous and lump-free. To prevent lumps from forming (very harmful with this type of product), start blending with just a little water so as to obtain a homogeneous, very viscous paste. After this, add more water to achieve the right consistency, which must be fluid/ viscous. Be careful not to add too much water as this would cause the leveling mortar to completely detach. Leave mixture to rest for 2-3 minutes, then scrape the bottom of the receptacle with a knife of trowel to make sure that the product has not separated. If this is the case, add more PLAN-10 powder to the mixture, briefly blend again and pour onto the substrate. Use blender at low speed (approx. 500 rpm) to mix the product as high speed will combine too much air into the mixture and impair the smoothness of the finish.

The product can also be pumped by machine. Comply with the machine manufacturer's instructions.

APPLICATION

PLAN-10 just needs to be spread with a smooth steel trowel followed by a spiked roller to break any air pockets. The layer must not be less than 2 mm thick. The product will begin to set after 20 min. and is treadable after approximately 3-4 hours.

WARNINGS AND RECOMMENDATIONS

- do not apply PLAN-10 in layers less than 3 mm thick if the floor must be covered with parquet
- do not apply to substrates subject to flexural stress
- do not use on substrates subject to continuous rising damp
- do not apply in layers more than 10 mm thick
- do not add anything to the product that is not specified in this data sheet
- do not use the product once it has started to set, by adding water to make it more workable. Prepare fresh mixture
- do not use on old wooden floors
- do not use outdoors
- do not apply at temperatures lower than 5°C or higher than 30°C

CONSUMPTION

1.4 Kg/m² per mm of thickness

plan-10

TECHNICAL DATA	VALUE	STANDARD
Appearance	Reddish powder	
Water required for mixing	6 I. per 25 kg bag	
Curing time	2 min	
Pot life	*20 min	
Minimum thickness	2 mm	
Maximum thickness	10 mm	
Treadable	after 3-4 h	
Can be covered	*after 24-36 h	
Compressive strength after 24 h	≥ 15 N/mm²	EN 13892-2
Compressive strength after 28 days	≥ 30 N/mm²	EN 13892-2
Flexural strength after 24 h	≥ 3.0 N/mm ²	EN 13892-2
Flexural strength after 28 days	≥ 7.0 N/mm ²	EN 13892-2
Thermal resistance	from -30°C to +80°C	

* these time intervals refer to a temperature of 23°C-50% R.H.. They become shorter with higher temperatures and longer at lower temperatures.

SPECIFICATION

Horizontal substrates must be leveled with fast-setting, cement-based self-leveling mortar such as TECHNOKOLLA's PLAN-10, which can be covered after 24 h. with resilient materials and parquet. The product must be certified as conforming to UPEC strength class P3.

Technokolla reminds you to examine the "**notes**" document that completes the information in this data sheet. The document can be downloaded in the pdf format from the website www.technokolla.com.

The advice about technical matters in the technical data sheets, or given verbally or in writing by our personnel as part of our customer assistance service, is the result of our best and most up to date experience. Since we are unable to personally modify the conditions in the building site or the way the work is carried out, this information is purely indicative and, thus, binds us neither legally nor in any other way in relation third parties. This information does not relieve the end user from being responsible for testing our products so as to make sure they are fit for the required use. We therefore strongly advise the customer/user to subject Technokolla's products to preventive tests in order to ensure that they are suitable. The end user is also responsible for checking to make sure that this technical data sheet is not obsolete and that more recent editions have not replaced it. Thus, before using our products, you are advised to download the most up to date version of the technical data sheet from our web site www.technokolla.com.





Sika Italia S.p.A. Registered Office and Administrative Headquarters: Via L. Einaudi 6, 20068 Peschiera Borromeo (MI) Sassuolo Plant (MO): Via Radici in Piano 558, Postal Code 41049 Tel: +39 0536 809711 Fax: +39 0536 809729 www.technokolla.com